

Thioplast EPS35

Liquid polysulfide polymer with epoxy end groups

Thioplast® EPS35 is a purely aliphatic epoxy-terminated polysulfide polymer. This worldwide unique product is used in combination with conventional epoxy resins to manufacture high-performance heavy-duty adhesives and coatings featuring excellent primerless adhesion, low-temperature impact and crack resistance, improved chemical resistance and anti-corrosion properties.

CAS number
2495231-87-1

Characteristics

Appearance	Clear amber liquid
Epoxy-oxygen content	approx. 2.0 – 2.7 wt%
Equivalent weight	600 - 800 g/equ
Viscosity, 25°C	approx. 3.5 Pa.s
Specific weight	1230 kg/m ³

Notes:

Typical properties, not to be construed as product specifications.

Applications

Thioplast® EPS35 is primarily used in metal or concrete coatings to improve the flexibility, impact and thermal shock resistance as well as the resistivity against chemicals, oils, corrosion and low-temperature cracks. Thioplast® EPS35 is compatible with most Bisphenol A, A/F, F and Novolac resins and can also be used in epoxy-based adhesives and sealant formulations. As with any product, the use of Thioplast® EPS35 in a given application must be tested (including, but not limited to field testing) in advance by the user to determine suitability. Thioplast® EPS35 is used in two-component systems. Typical curatives are linear or cyclic aliphatic or aromatic amines.

Storage

Thioplast® EPS35 is a reactive Pre-polymer. Protection against contact with air, moisture and temperatures over 25°C (77°F) during transportation and storage is needed. Containers should be firmly closed after each use. Under appropriate storage conditions the shelf life of this product is 12 months.

Packaging and transport

Thioplast® EPS35 is available in 200 l drums or 1000 l IBC. Other packages available on request.

Safety and handling

Full information on the safe handling is available in the Safety Data Sheet (SDS). Further details are available upon request.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Thioplast® is a registered trademark of Nouryon Chemicals B. V. or affiliates in one or more territories.

Contact Us

Nouryon Pulp and Performance Chemicals AB

13000

SE-850 13 Sundsvall

Sweden

+46 60 13 4000

+46 60 56 9518 (Fax)

info.expancel@nouryon.com

The Nouryon logo consists of a stylized blue 'N' followed by the word 'ouryon' in a lowercase, sans-serif font.